



THERMAL CONDUCTIVITY TEST

The thermal conductivity test was conducted in compliance with **JIS A 1412**.

Product characteristic: cement, a siliceous material, a mixture as a main raw material, and others.

Product selected: Nichiha 16 mm thick product.

		°C	[W/(M·K)]	[Kcal/(m·hr·°C)]
1	NICHIHA EX SERIES	21,13	0,259	0,223
2	NICHIHA EX SERIES	20,98	0,258	0,222
3	NICHIHA EX SERIES	20,98	0,257	0,221